

Specification	Acceptable Range	Result	Test Method	Explanations
<b>Absolute Viscosity</b>	Min 2400	2486	ASTM – D4402	at 60°C , Poises
<b>Kinematic Viscosity</b>	Min 350	378	ASTM – D4402	at 135°C , c.st
<b>Ductility</b>	Min 100	>100	ASTM – D113	at 25°C , cm
<b>Solubility</b>	99.0 Min	99.8	ASTM – D2042	in CCL4 , %
<b>Specific Gravity</b>	1.01-1.06	1.014	ASTM – D70	at 25°C
<b>Spot Test</b>	Negative	Negative	T102	in Naphtha
<b>Flash Point</b>	220 Min	342	ASTM – D92	°C
<b>Penetration</b>	50-70	66	ASTM – D5	at 25°C , mm/10
<b>Softening Point</b>	Min 47	49.5	ASTM – D36	°C
<b>Test on Residue From Thin Film Oven Test (T.F.O.T)</b>				
<b>Raito Viscosity</b>	Max 4.0	2.1	ASTM – D4402	at 60°C , %
<b>Ductility</b>	Min 40	63	ASTM – D113	at 25°C , cm